



FORCE 842[®]

DRY MOLY LUBRICANT



FEATURES

- Works under extreme temperatures (842°F) & pressures (100,000 psi)
- Dry film resists dirt & dust
- Provides excellent water & chemical resistance
- High adhesion
- Use for assembly & break-in lubrication
- Prevents seizures

Conforms to: Mil-L-46147A Type II
Federal Test Method No. 791, Method 4001
Salt Spray Corrosion Protection

APPLICATIONS

- Aircraft Landing Gear
- Brake Adjustment Screws
- Forklift Channels
- Fire Doors
- Oven Chains & Cables
- Oven Dolleys
- Overhead Crane Rails
- Planting Hooks in Ovens
- Sliding Surfaces
- Rollers

PROPERTIES

Appearance/Physical State:
Dark gray coating

Dry to Touch:
2 – 3 minutes

Falex Break-Down Load:
2500 lbs.

Propellant:
Isobutane/Propane

Temperature Range:
0°F – 842°F (-18°C – 450°C)

Solid Lubricant:
Molybdenum Disulfide

Specific Gravity (water=1):
0.74 – 0.76

% Non-Volatiles:
5%



MATERIAL SAFETY DATA SHEETS AVAILABLE UPON REQUEST OR VISIT OUR WEB SITE : WWW.LPSLABS.COM

PACKAGE

Net Fill
11 oz. (312 grams) aerosol

Part No.
02516

LPS Laboratories • An Illinois Tool Works Company

P.O. Box 105052 • 4647 Hugh Howell Road • Tucker, GA 30085-5052 • TEL: (800) 241-8334 or (770) 243-8800 • FAX: (800) 543-1563 or (770) 243-8899

Internet Web Site: www.lpslabs.com

©2007 LPS Laboratories • LPS[®] is a registered trademark of Illinois Tool Works • Printed in U.S.A. • All Rights Reserved • Form #2221 • Rev. 12/2007