



# BRIGHTCOAT

## COLD GALVANIZE CORROSION INHIBITOR



Qualified to: ASTM A-780

### PACKAGE

Net Fill

13 oz. (368 grams) aerosol

Part No.

05916

### FEATURES

- Shiny zinc coating
- Prevents rust and corrosion on all metals
- Restores hot dip galvanizing
- Dries to touch in 15 to 30 minutes
- Repairs rusted, galvanized and welded surfaces
- Electrochemically protects bare metal
- Heat resistant, flexible coating
- Will not yellow, chalk, crack or peel
- Meets or exceeds these specifications: ASTM A-780



### APPLICATIONS

- Air Conditioning Parts
- Chain Link Fences
- Ducts
- Heating Parts
- Machine Housing
- Material Handling Equipment
- Newly Welded Surfaces
- Outside Storage Tanks
- Pipes
- Plumbing
- Pulley and Chain Cover
- Structural Steel

### PROPERTIES

Color:

Reflective Silver-Gray

Coverage:

25–30 sq.ft./ can

Dries to Touch:

15–30 minutes

Dry Film Thickness:

0.6 mils (single application)

Flash Point:

< 0°F (-17°C)

Recoat Time:

6 hours

Solids Content:

18–19%

Specific Gravity:

0.93–0.99

V.O.C. Content:

30–32%

Zinc Content of Dry Film:

67–69%

MATERIAL SAFETY DATA SHEETS AVAILABLE UPON REQUEST OR VISIT OUR WEB SITE : [WWW.LPSLABS.COM](http://WWW.LPSLABS.COM)

**LPS Laboratories** • An Illinois Tool Works Company

P.O. Box 105052 • 4647 Hugh Howell Road • Tucker, GA 30085-5052 • TEL: (800) 241-8334 or (770) 243-8800 • FAX: (800) 543-1563 or (770) 243-8899

**Internet Web Site: [www.lpslabs.com](http://www.lpslabs.com)**

©2009 LPS Laboratories • LPS®, PT® and PF® are registered trademarks of Illinois Tool Works • Printed in U.S.A. • All Rights Reserved • Form #2176 • Rev. 9/2009