



Gillfab™ 1367 Laminate

December 2002

Description

Gillfab 1367 is a very high impact resistant, low smoke and toxicity, fiberglass reinforced phenolic laminate.

Applications

Aircraft cargo compartment liner.

Features

- High mechanical strength, puncture resistance and corrosion resistance.
- Service temperature range: To 220F.
- White Tedlar overlay on face side for surface reflectivity.

Specifications

- Boeing BMS 8-223 CI 2 Gr B, all types
- McDonnell Douglas specification DMS 2419 Ty 50-90
- LAC-C-22-1249 CI 3
- FAR Part 25 Appendix F Parts I and III (Burn Through)
- ATS 1000.001.

Availability

Thickness:	.013", .020", .030", .040", .050" and .070"
Length:	Up to 168". Also available in rolls up to 150' (if .030" or thinner and 60" or narrower).
Width:	Up to 72".
Color:	White on face side, amber on back side.



Construction

Resin: Modified phenolic.
Reinforcement: Woven glass cloth.
Surface: 1 mil Tedlar overlay.

Standard Tolerances

Thickness:	+/- .003" (.013" and .020"); all other \pm 10%
Length:	+ 0.5", - 0"
Width:	+ 0.5", - 0"
Warp Twist:	3% of dimension measured

Alternative Gill Products

Product Number	Difference
Gilliner 1367B	Equivalent mechanical properties with 20-25% weight savings over 1367/1367A. Qualified to BMS 8-223 CI 4 Gr A.
Gillfab 1366	High impact resistant cargo liner. Polyester resin system has higher smoke emission; qualified to Boeing Specification BMS 8-2 CI 2 Gr B.
Gillfab 1367A	Similar to 1367, but lower impact resistance.
Gillfab 1367C	Same as 1367A but manufactured in roll stock in lengths up to 150' and up to .030" thick



Properties of Gillfab 1367

Typical Average Property Values

Property	Test Method	Unit	Type 13	Type 20
Weight	BMS8-223	lb/sq ft (kg/sq m)	0.121 (.59)	0.195 (0.95)
Thickness	BMS8-223	inch (mm)	0.013 (0.33)	0.021 (0.53)
Water Absorption	FTMS 406-7031	%	.8	1.1
Impact	BMS8-223 TESTER #3	ft-lb (N-m)	11 (14.9)	15 (20.4)
Impact	DMS2419	ft-lb (N-m)	>32 (>43.4)	>40 (>54.3)
Drum Peel Note 1 Warp Fill	BMS8-223	in-lb (N-m)/3 in width in-lb (N-m)/3 in width	56 (6.3) --	55 (6.2) 66 (7.5)
Edge Bearing Warp Fill	BMS8-223	ksi (MPa) ksi (MPa)	37 (254) 34 (235)	39 (268) 36 (249)
Tedlar Peel Warp Fill	BMS8-223	lb/in (kg/m) lb/in (kg/m)	3.0 (54) 2.6 (46)	3.7 (66) 2.7 (48)
Flexural Note 2 Strength Modulus	MIL-STD-401B	ksi (MPa) msi (GPa)	NR NR	27 (184) 2.1 (14.2)
Tensile Note 2 Strength Modulus	DMS 2226	ksi (MPa) msi (GPa)	54.5 (375.8) 3.16 (21.8)	60.6 (417.8) 2.5 (17.2)
Bolted Joint Strength	DMS 2226	lb (N)	103.3 (46.9)	193 (87)
Flammability - 60 Second Vertical Self-Extinguishing Time Burn Length Drip Extinguishing Time	BMS 7230	second inch (mm) second	0 2.3 (57) None	0 2.7 (68) None
Flammability - 45 Degree Self-Extinguishing Time Glow Time Penetration	DMS 1508	second second ---	0 1.7 None	0.5 1.8 None
Smoke Density	ASTM 662	D _s	21.7	35.3
Oil Burner Note 3	FAR 25.855	---	Pass	Pass
<p>Note 1 - On Type 13, drum peel in the fill direction resulted in fabric tearing and no data could be obtained.</p> <p>Note 2 - Reported only in warp direction.</p> <p>Note 3 - Test performed by U. S. Testing in accordance with the procedure outlined in Appendix F, Part III of FAR 25.855, "Oil Burner - Burn through Resistance".</p> <p>NR = No Requirement</p>				



Property	Test Method	Unit	Type 30	Type 40
Weight	BMS8-223	lb/sq ft (kg/sq m)	0.293 (1.43)	0.375 (1.83)
Thickness	BMS8-223	inch (mm)	0.031 (0.79)	0.040 (1.02)
Water Absorption	FTMS 406-7031	%	0.9	1.1
Impact	BMS8-223 TESTER #3	ft-lb (N-m)	19 (25.8)	25 (33.9)
Impact	DMS2419	ft-lb (N-m)	>50 (>67.8)	>50 (>67.8)
Drum Peel Warp Fill	BMS8-223	in-lb (N-m)/3 in width in-lb (N-m)/3 in width	16 (21.7) 24 (32.6)	15.7 (21.3) 15.7 (21.3)
Edge Bearing Warp Fill	BMS8-223	ksi (MPa) ksi (MPa)	40 (275) 38 (262)	42 (290) 40 (275)
Flexural Note 1 Strength Modulus	MI-STD-401B	ksi (MPa) msi (GPa)	39.1 (267) 2.57 (17.7)	NR NR
Tedlar Peel Warp Fill	BMS8-223	lb/in (kg/m) lb/in (kg/m)	3.2 (57.1) 2.8 (50)	3.9 (69.6) 4.2 (75.0)
Tensile Note 1 Strength Modulus	DMS 2226	ksi (MPa) msi (GPa)	57.9 (399.2) 2.50 (17.2)	NR NR
Bolted Joint Strength	DMS 2226	lb (N)	286.9 (130.3)	NR
Flammability -60 Second Vertical Self-Extinguishing Time Burn Length Drip Extinguishing Time	BMS 7230	second inch (mm) second	0 2.6 (65) None	0 1.7 (44) None
Flammability - 45 Degree Self-Extinguishing Time Glow Time Penetration	DMS 1508	second second ---	0 1.7 None	0 0 None
Smoke Density	ASTM 662	D _s	31.6	42.8
Oil Burner - Note 2	FAR 25.855	---	Pass	Pass
Note 1 - Reported only in warp direction. Note 2 - Test performed by U. S. Testing in accordance to the procedure outlined in Appendix F, Part III of FAR 25.855, "Oil Burner - Burn through Resistance". NR = No Requirement				



Property	Test Method	Unit	Type 50	Type 70
Weight, psf	BMS8-223	lb/sq ft (kg/sq m)	0.465 (2.27)	0.658 (3.21)
Thickness, in.	BMS8-223	inch (mm)	0.050 (1.27)	0.065 (1.65)
Water Absorption	FTMS 406-7031	%	1.25	1.0
Impact	BMS8-223 TESTER #3 DMS2419	ft-lb (N-m)	37 (50.165)	47 (63.723)
Edge Bearing Warp Fill	BMS8-223	ksi (MPa) ksi (MPa)	42,000 (290) 40,000 (275)	47,000 (324) 45,000 (310)
Tedlar Peel Warp Fill	BMS8-223	lb/in (kg/m) lb/in (kg/m)	0 (0) 0 (0)	0 (0) 0 (0)
Flammability -60 Second Vertical Self-Extinguishing Time Burn Length Drip Extinguishing Time	BMS 7230	second inch (mm) second	3.0 1.6 No Drips	3.0 1.3 No Drips
Smoke Density	ASTM 662	D _s	45	47
Oil Burner - Note 1	FAR 25.855	---	Pass	Pass

Note 1 - Test performed by SGS/US. Testing in accordance with the procedure outlined in Appendix F, Part III of FAR 25.855, "Oil Burner - Burn through Resistance".

M.C. Gill Corporation gives no warranties, expressed, implied or statutory, or otherwise, as to the description, quality, fitness, capacity, or any other matter, of the properties described. The data given represents minimum values to be expected. Through additional testing of each lot it is possible to verify that the product exceeds the tabulated values. It is recommended, however, that prospective users evaluate the materials to determine their suitability for the users' specific requirements. Values are given on the condition that the user assumes all risk and that responsibility for any loss or damage caused by or resulting from the use of such information is disclaimed by M.C. Gill Corporation.

M.C. Gill Corporation
4056 Easy Street
El Monte, CA 91731-1087 USA
626-443-4022 info@mcgillcorp.com

M.C. Gill Europe Ltd. - Insoleq
23 Enterprise Road, Balloo Industrial Estate South
Bangor Co-Down BT19 7TA, Northern Ireland
+44 (0) 2891 470073 sales@insoleq.co.uk

www.mcgillcorp.com

© M.C. Gill Corporation. All rights reserved.

